

Weighted averages from ARD-10-001

Zone	From meters	To meters	Interval meters	Zn%	Cu%	Pb%	Au g/t	Ag g/t
Oxide-sulphide transition	63.00	73.00	10.00	1.22	1.89	0.04	0.92	21
Sulphide	73.00	80.00	7.00	15.15	0.99	0.32	0.39	33

NOTE: The above intervals are drill hole lengths. There is currently insufficient information to determine the true widths of the intervals

ARD-10-03

From(m)	To (m)	Interval(m)	Cu %	Zn %	Pb%	Au g/t	Ag g/t
60.00	64.00	4.00	0.849	0.076	0.006	0.280	17
64.00	68.00	4.00	0.149	0.028	0.003	0.078	5
68.00	81.00	13.00	3.309	5.593	0.068	1.848	46
81.00	84.40	3.40	0.308	8.200	0.062	0.248	12

ARD-10-04

From(m)	To (m)	Interval(m)	Cu%	Zn %	Pb%	Au g/t	Ag g/t
108.00	112.00	4.00	3.492	0.314	0.027	0.685	38
112.00	115.20	3.20	1.795	5.134	0.100	0.219	27
115.20	118.00	2.80	0.078	0.306	0.007	0.037	5
118.00	125.00	7.00	2.697	1.703	0.021	0.824	26